

1. DESCRIPTION

Weldable steel wire with Boron in coils for thin drawing. Material according to ISO 16120-3 C4D1, ASTM A510M - SAE1005 and SAE1006 standard.

2. HEAT CHEMICAL COMPOSITION

	C %	Mn %	Si %	P %	S %	B %	Cu %
min	-	0.25	-	-	-	0.008	-
max	0.05	0.35	0.10	0.015	0.020	0.010	0.20

Product analysis deviations according to ISO 16120-3 and ASTM A510M.

3. MECHANICAL AND DIMENSIONAL PROPERTIES

Tensile strength: Rm [MPa] ≤ 370

Elongation: A10 [%] ≥ 35

Diameter range: 5,5 – 21,5 mm

Diameter tolerance and out-of-round: according to ISO 16124 grade T2 and ASTM A510M.

Diameter [mm]	5,5 ÷ 10	11 ÷ 15	16 ÷ 21,5
Tolerance [mm]	±0,25	±0,30	±0,35
Out-of-round max [mm]	0,40	0,48	0,56

Any geometric defect regarding the tail of the coils could occur within a distance from the end of wire rod greater than those included in ISO 16124 Table 11.

4. SURFACE AND INTERNAL QUALITY

Surface quality: according to ISO 16120-2 par. 4.3 and 4.4 – maximum defect depth 0,20 mm.

Internal quality: absence of defects compromising use (ISO 16120-2 par. 4.5).

5. STANDARD PACKING

In coils up to approx. 2500 kg, inside diameter about 800 mm, outside diameter about 1200 mm, maximum length 1900 mm.

6. STANDARD IDENTIFICATION

Each coil with label reporting: Heat number, nominal diameter, steel quality (grade), weight and date of rolling. Additional colored label to distinguish different heats.

7. STANDARD CERTIFICATION

On demand Inspection Certificate according to EN 10204 3.1.



Acciaierie di Verona S.p.A.
Plant
Lungadige A. Galtarossa,
21/c
37133 Verona
Tel.: +39 045 805111
Fax: +39 045 591564

Registered Office
Z.I. Rivoli
33010 Osoppo (UD)
Tel.: +39 0432 062811
Fax: +39 0432 062812
www.pittini.it